

What Is Claimed Is:

1. A coating composition for undercoat comprising:

(A) an acrylic resin having a hydroxyl value of 30 to 85 and a weight average molecular weight of 1000 to 30000,

(B) a pigment,

(C) resin fine particles,

(D) a polyisocyanate compound, and

(E) a curing catalyst; wherein:

a ratio of isocyanate group in the (D) component to 1 equivalent of hydroxyl group in the (A) component is 2.0 to 4.0 equivalents;

content of the (B) component is from 100 to 500 parts by weight relative to 100 parts by weight of resin solid matter; and

the (C) component is mixed so as to be from 0.1 to 5% by weight as a solid matter relative to the weight of the (B) component.

2. The coating composition for undercoat according to claim 1, wherein the acrylic resin (A) is a resin obtainable by polymerizing an acrylic monomer having hydroxyl group as an essential monomer and other acrylic monomer and/or a vinyl monomer.

3. A coating method for repair comprising steps of:

conducting surface treatment at a part to be repaired;  
providing undercoat; and providing topcoat; wherein a coating  
composition for the undercoat comprises: (A) an acrylic resin  
having a hydroxyl value of 30 to 85 and a weight average  
5 molecular weight of 1000 to 30000, (B) a pigment, (C) resin  
fine particles, (D) a polyisocyanate compound, and (E) a  
curing catalyst; wherein:

a ratio of isocyanate group in the (D) component to  
1 equivalent of hydroxyl group in the (A) component is 2.0 to  
4.0 equivalents;

content of the (B) component is from 100 to 500  
parts by weight relative to 100 parts by weight of the resin  
solid matter; and

the (C) component is mixed so as to be from 0.1 to  
5% by weight as a solid matter relative to the weight of the  
(B) component.